

Certain chemicals that may exist in end-user locations release airborne contaminants that can impact the integrity and safety of key fixture components that contain acrylic or polycarbonate material. Immediate damage may occur such as crazing, cracking, permeation losses and mechanical failure. Products with visually noticeable deterioration have diminished integrity and must be replaced immediately with a more suitable product for the application.

The following tables identify the most common chemicals and is not intended to be all-inclusive. Exposure to compounds identified as "Not Acceptable" will void all warranties associated with the product. Acrylic or polycarbonate components should not be used in areas where these chemicals are used and where these chemicals become mists or airborne vapors. Ensure that chemical interactions are considered when selecting fixtures. For additional information please consult an authorized factory representative.

The statements, technical information and recommendations obtained herein are believed to be accurate as of June 1, 2009. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Acuity Brands Lighting expressly disclaims any and all liability. NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The user should thoroughly test any application before commercialization.

Rating is based on visual appearance at ambient temperature 68°F, 50% humidity. Consult factory where applicable. All technical information is believed to be accurate as of June 1, 2009.

ACRYLIC ENVIRONMENTAL COMPATIBILITY

NOT ACCEPTABLE				
Acetaldehyde	Cinnamon Oil	Methyl Salicyclate		
_ Acetates	Cloves	Methylamine		
Acetic Acid, 50%+	Cosmoline Removers	Methylene Dichloride		
Acetic Anhydride	Cresol	Mineral Oil @ 40°C+		
Acetone	Cyclohexane	Nail Polish		
Acetonitrile	Cyclohexanone	Naphtha		
Acetophenone	Cyclohexene	n-butyric Acid, 100%		
Acrylic Paints	Diacetone Alcohol	Nitric Acid, 40%+		
Alcohol, Allyl	Diamyl Phthalate	Nitrobenzene		
Alcohol, Amyl	Dibutyl Sebacate	Nitrocellulose		
Alcohol, Benzyl	Diethyl Ether	n-Octane		
Alcohol, Butyl (Butanol)	Dimethyl Formamide	Oleum		
Alcohol, Ethyl (Ethanol), 50%+	Dioctyl Sebacate	Organic Solvents		
Alcohol, Isopropyl	Dioxane	Paint Removers		
Alcohol, Methyl (Methanol), 10%+	Ether	Paint Thinner		
Aluminum Hydroxide	Ethyl Acetate	Perchlorethylene		
Amyl Acetate	Ethyl Bromide	Petroleum Ether (100-120°C)		
Ammonia @ 40°C+	Ethyl Butyrate	_ Phenols		
Aniline	Ethylene Bromide	Phosphoric Acid, 95%		
Aromatic Solvents	Ethylene Chloride	Phosphoric Trichloride		
Aviation Fuel (100 Octane)	Ethylene Dibromide	_ Phthalates		
Benzaldehyde	Ethylene Oxide (Moist)	Pyridine		
Benzene	_ Fluorides	Salicylic Acid		
Benzoic Aldehyde	Formic Acid	Silicon Tetrachloride		
Bituminous Emulsions	Fuels w/ Benzene (Gasoline)	Sodium Phosphate		
Brake Fluid	Glycol	Sulfoxides		
Bromine Gas	Hydrofluoric Acid	Sulfur Dioxide, Liquid		
Butraldehyde	Hydrochloric Acid, 40%+	Sulfuric Acid, 65% @ 40°C+		
Butyl Acetyl Ricinoleate	Hydrogen Peroxide, 40%+	Sulfurous Acid, Concentrated		
Butyl Lactate	Iron Perchloride	Tincture of lodine, 5%		
Butyl Stearate	lsoctane	Toluene		
Carbolic Acid	_ Ketones	Transformer Oil		
Carbon Disultide	 Lacquer Thinner	Trichloraethane		
Carbon Tetrachloride	Lactic Acid Butyl Ester	Trichloroacetic Acid		
Cellulose Paints	Mercury Chloride	Trichloroethylene		
Chlorinated Hydrocarbons	Meta-Cresol	Turpentine		
Chlorinated Solvents	Methyl Benzoate	Vegetable Oil		
Chlorine Gas	Methyl Chloride	Xylene		
Chlorophenol	Methyl Cycohexanol	,		
Chromic Acid	Methyl Naphthalene			

Catalog Number

Туре

Notes

Acrylic & Polycarbonate Compatibility

	ACCEPTABLE	
2-Ethylhexyl Sebacate	Fruit Juice	Potassium Chlorate
Acetic Acid, 5%	Glycerol (Glycerine)	Potassium Cyanide
Ammonia-Based Cleaners @ 25°C	Heptane	Potassium Dichromate, 10%
Ammonia @ 25°C	Hexane	Potassium Hydroxide @ 25°C
Ammonium Hydroxide, 28%	Hydrochloric Acid, 38%	Potassium Permanganate
Ammonium Nitrate	Hydrogen Peroxide, 30%	Potassium Sulfite
Ammonium Phosphate	Hydrogen Sulfide	Power Steering Fluid
Aniseed, Bay Leaves, Nutmeg	Kerosene	Propylene
Anti-freeze	Lactic Acid, 20%	Pure-oil Paints
Beer	Metal Carbonates	Silicone Oil
Bleaching Powder Paste	Metal Chlorides	Silver Nitrate
Bleaching Powder Solution, 5%	Metal Sulfates	Soap Suds
Butane	Methane Gas	Sodium Chloride, 10%
Calcium Hypochlorite	Milk	Sodium Cyanide
Car Wash Detergent	Motor Oil	Sodium Fluoride
Carbon Dioxide Gas	Natural Gas	Sodium Hydroxide, 60%
Carbon Monoxide Gas	Nitric Acid, 20%	Sodium Hypochlorite, 15%
Caustic Potash	Nitric Oxide	Sodium Nitrate
Chlorine Based Cleaners @ 25°C	Nitrogen Dioxide Gas	Sodium Thiosulphate, 40%
Chlorine, Aqueous, 2%	Nitrogen Monoxide Gas	Stearic Acid
Citric Acid, 20%	Olefric Carbolic Acids	Sulfur Dioxide, Dry Gas
Coffee (Unflavored)	Oleic Acid	Sulfuric Acid, 30% @ 25°C
Cooking Oil	Olive Oil	Sulfurous Acid, 5%
Cottonseed Oil	Oxalic Acid, 100%	Tartaric Acid, 50%
Diethylene Glycol	Oxygen Gas	Transmission Fluid
Epoxy Adhesives	Ozone Gas	Tricresyl Phosphate
Ethyl Alcohol, 15%	Paraffin, Medicinal	Triethyl Amine
Ethylene Glycol	Pepper, Onions	Vinegar
Ethylene Oxide (Dry)	Phosphoric Acid, 10%	Wax Polish
Ferric Chloride, Aqueous, 10%	Photographic Baths	Whitewash
Formaldehyde, Aqueous, 40%	Polishing Compounds	Wine

POLYCARBONATE ENVIRONMENTAL COMPATIBILITY

NOT ACCEPTABLE			
Acetaldehyde, 100%	Chromic Acid	Methylene Dichloride	
_Acetates	Clove Oil	Mineral Oil @ 40°C+	
Acetic Acid, Glacial, 100%	Cosmoline Removers	Mineral Spirits	
Acetic Anhydride	Cresol	Nail Polish	
Acetone	Cutting Fluids and Oils	Naphtha (Petroleum Ether)	
Acetonitrile	Cyclohexanone	Naphthenic Acids	
Acetophenone	Cyclohexene	n-butyric Acid, 100%	
Alcohol, Allyl	Diamyl Phthalate	Nitric Acid, 25%+	
Alcohol, Amyl	Dibutyl Sebacate	Nitrobenzene	
Alcohol, Benzyl	Diethyl Ether	n-Octane	
Alcohol, Ethyl (Ethanol), 50%	Dimethyl Formamide	Oleum	
Alcohol, Isopropyl, 100%	Dioctyl Sebacate	Paint Removers	
Alcohol, Methyl (Methanol), 50%	Dioxane	Paint Thinner	
Aluminum Hydroxide	Ether	Perchlorethylene	
_Amines	Ethyl Acetate	Phenols	
Ammonia	Ethyl Alcohol, Concentrated	Phenol, Aqueous, 5%	
Ammonium Hydroxide	Ethyl Bromide	_Phthalates	
Amyl Acetate	Ethyl Butyrate	Potassium Hydroxide (Potash)	
Aniline	Ethylene Bromide	Propane	
Aromatic Hydrocarbons	Ethylene Dibromide	Pyridine	
Aviation Fuel	Ethylene Oxide	Sodium Hydroxide	
Benzaldehyde	Freon	Sodium Hypochlorite, 30%	
Benzene	Fuels w/ Benzene (Gasoline)	Sodium Nitrate	
Benzoic Aldehyde	Glass Cleaners	Sodium Sulfide	
Brake Fluid	Hydrochloric Acid, 25%+	_Sulfoxides	
Bromine	Hydrofluoric Acid	Sulfur Dioxide	
Butadiene	Hydrogen Peroxide, 40%+	Sulfuric Acid, 70%+	
Butane	lsoctane	Sulfurous Acid	
Butyl Acetyl Ricinoleate	Kerosene	Tea	
Butyl Stearate	_Ketones	Tincture of lodine, 5%	
Calcium Hypochlorite	Lacquer Thinner	Toluene	
Carbolic Acid	Lactic Acid Butyl Ester	Transformer Oil	
Carbon Disulfide	Meta-Cresol	Trichloroacetic Acid	
Carbon Tetrachloride	Methyl Benzoate	Trichloroethane	
Cellulose Paints	Methyl Chloride	Trichloroethylene	
Chlorinated Hydrocarbons	Methyl Cycohexanol	Triethanalomine	
Chlorinated Solvents	Methyl Ethyl Ketone	Turpentine	
Chlorine	Methyl Naphthalene	Urea	
Chlorophenol	Methyl Salicyclate	Xylene	
Diacetone Alcohol	Methylamine		

ACCEPTABLE				
Acetic Acid, 5%	Hydrochloric Acid, 15%	Silicone Oil		
Ammonium Chloride	Hydrogen Peroxide, 30%	Silver Nitrate		
Ammonium Phosphate	Lactic Acid, 20%	Soap Solutions		
Ammonium Sulfate	Linseed Oil	Sodium Bicarbonate		
Aniseed, Bay Leaves	Metal Carbonates	Sodium Chlorate		
Anti-freeze	Metal Chlorides	Sodium Chloride, 10%		
Beer	Metal Sulfates	Sodium Hypochlorite, 15%		
Benzoic Acid	Methane Gas	Sodium Peroxide		
Bleaching Powder Solution, 2%	Milk	Sodium Thiosulphate, 40%		
Boric Acid, 10%	Mineral Oil @ 25°C	Stearic Acid		
Car Wash Detergent	Motor Oil	Sulfur Dioxide, Dry Gas		
Carbon Dioxide	Natural Gas	Sulfuric Acid, 30%		
Carbon Monoxide	Nitric Acid, 10%	Sulfurous Acid, 5%		
Carbonic Acid	Nitrogen Dioxide Gas	Tannic Acid, 10%		
Chlorine-base Cleaners (Clorox)	Oleic Acid	Tartaric Acid, 50%		
Cinnamon, Onions	Olive Oil	Transmission Fluid		
Citric Acid, 10%	Oxalic Acid, 100%	Tripropylene Glycol		
Cooking Oil	Oxygen	Vegetable Oils		
Cottonseed Oil	Paraffin, Medicinal	Vinegar		
Cyclohexane	Phosphoric Acid, 30%	Water, Mineral Water		
Diethylene Glycol	Photographic Baths	Wax Polish		
Epoxy Adhesives	Polishing Compounds	Wine		
Ethyl Alcohol, 15%	Potassium Bromate	Zinc Sulfate		
Ethylene Glycol E	Potassium Bromide			
Fatty Acids @ 25°C	Potassium Chlorate			
Ferric Chloride, Aqueous, 10%	Potassium Dichromate, 10%			
Formaldehyde, Aqueous, 40%	Potassium Permanganate			
Fruit Juice	Potassium Sulfate			
Glycerol, Glycerine	Power Steering Fluid			
Heptane	Propylene			
Hexane @ 25°C	Salicyclic Acid @ 25°C			



ACRYLIC-POLY-COMPATIBILITY